



ANNEAU À SOUDER 45° EN ACIER BRUT

DESCRIPTIF

Acier brut noir

Prêt à être soudé

Marquage : CE, CMU, Fabricant, matière



INFORMATIONS

- Coefficient de sécurité : 5 fois la CMU
- Disponible à 45°




Délais 24/48h
- EXPRESS -



CERTIFICAT DE
CONFORMITÉ

CAP LEVAGE



RÉFÉRENCE	CMU	DIA	A	B	C	D	E	POIDS
	kg	mm	mm	mm	mm	mm	mm	kg
ASL500	500	12	31	55	13	89	82	0.16
ASL1000	1000	14	42	69	13	113	101	0.3
ASL2000	2000	18	45	81	18	134	123	0.5
ASL3000	3000	21	57	97	19	152	140	0.8
ASL4000	4000	24	65	113	23	167	155	1.2
ASL6000	6000	28	83	140	31	218	205	2.36